

Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

頁數(Page): 1 of 15

以下測試樣品係由申請廠商所提供及確認 (The following sample(s) was/were submitted and identified by/on behalf of the applicant as):

送樣廠商(Sample Submitted By)

南亞塑膠工業股份有限公司 (NAN YA PLASTICS CORPORATION)

日期(Date): 2017/02/15

樣品名稱(Sample Description)

NAN YA PE INDUSTRY FILM (南亞工業用PE膠膜)

收件日期(Sample Receiving Date)

2017/02/07

號碼(No.): CE/2017/21498

測試期間(Testing Period)

2017/02/07 TO 2017/02/14

測試需求(Test Requested):

(1) 依據客戶指定,參考RoHS 2011/65/EU Annex II及其修訂指令(EU) 2015/863測試鎘、鉛、汞、六價鉻、多溴聯苯、多溴聯苯 ™, DBP, BBP, DEHP, DIBP. (As specified by client, with reference to RoHS 2011/65/EU Annex II and amending Directive (EU) 2015/863 to determine Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP, DEHP, DIBP contents in the submitted sample.)

(2) 其他測試項目請見下一頁 . (Please refer to next pages for the other item(s).)

測試結果(Test Results) :

請見下一頁 (Please refer to next pages).

結論(Conclusion)

(1) 根據客戶所提供的樣品,其鎬、鉛、汞、六價鉻、多溴聯苯、多溴聯苯醚, DBP, BBP, DEHP, DIBP的 測試結果符合RoHS指令暨(EU) 2015/863之限值要求. (Based on the performed tests on submitted samples, the test results of Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP, BBP, DEHP, DIBP comply with the limits as set by RoHS and amending Directive (EU) 2015/863.)

Signed for and on beha SĞS TAIWAN LTD. Chemical Laboratory - Taipei

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-



Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號 NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN



頁數(Page): 2 of 15

測試結果(Test Results)

測試部位(PART NAME)No.1 : 透明塑膠膜(TRANSPARENT PLASTIC FILM)

號碼(No.): CE/2017/21498

測試項目 (Test Items)	單位 (Unit)	測試方法 (Method)	方法偵測 極限值 (MDL)	結果 (Result) No.1	限值 (Limit)
鎬 / Cadmium (Cd)	mg/kg	參考IEC 62321-5 (2013),以感應耦合 電漿原子發射光譜儀檢測. / With	2	n. d.	100
鉛 / Lead (Pb)	mg/kg	reference to IEC 62321-5 (2013) and performed by ICP-AES.	2	n. d.	1000
汞 / Mercury (Hg)	mg/kg	參考IEC 62321-4 (2013),以感應耦合 電漿原子發射光譜儀檢測. / With reference to IEC 62321-4 (2013) and performed by ICP-AES.	2	n. d.	1000
六價鉻 / Hexavalent Chromium Cr(VI)	mg/kg	参考IEC 62321 (2008),以UV-VIS檢 測. / With reference to IEC 62321 (2008) and performed by UV-VIS.	2	n. d.	1000
多溴聯苯總和 / Sum of PBBs	mg/kg	参考IEC 62321-6 (2015),以氣相層析 /質譜儀檢測. / With reference to IEC 62321-6 (2015) and performed by GC/MS.	-	n. d.	1000
一溴聯苯 / Monobromobiphenyl	mg/kg		5	n. d.	_
二溴聯苯 / Dibromobiphenyl	mg/kg		5	n. d.	-
三溴聯苯 / Tribromobiphenyl	mg/kg		5	n. d.	-
四溴聯苯 / Tetrabromobiphenyl	mg/kg		5	n. d.	-
五溴聯苯 / Pentabromobiphenyl	mg/kg		5	n. d.	_
六溴聯苯 / Hexabromobiphenyl	mg/kg		5	n. d.	-
七溴聯苯 / Heptabromobiphenyl	mg/kg		5	n. d.	-
八溴聯苯 / Octabromobiphenyl	mg/kg		5	n. d.	-
九溴聯苯 / Nonabromobiphenyl	mg/kg		5	n. d.	-
十溴聯苯 / Decabromobiphenyl	mg/kg		5	n. d.	-

日期(Date): 2017/02/15



Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

號碼(No.): CE/2017/21498

頁數(Page): 3 of 15

測試項目 (Test Items)	單位 (Unit)	測試方法 (Method)	方法偵測 極限值 (MDL)	結果 (Result) No.1	限值 (Limit)
多溴聯苯醚總和 / Sum of PBDEs	mg/kg		-	n. d.	1000
一溴聯苯醚 / Monobromodiphenyl ether	mg/kg		5	n. d.	-
二溴聯苯醚 / Dibromodiphenyl ether	mg/kg		5	n. d.	-
三溴聯苯醚 / Tribromodiphenyl ether	mg/kg		5	n. d.	-
四溴聯苯醚 / Tetrabromodiphenyl ether	mg/kg	參考IEC 62321-6 (2015),以氣相層析	5	n. d.	-
五溴聯苯醚 / Pentabromodiphenyl ether	mg/kg	/質譜儀檢測. / With reference to	5	n. d.	-
六溴聯苯醚 / Hexabromodiphenyl ether	mg/kg	IEC 62321-6 (2015) and performed by GC/MS.	5	n. d.	-
七溴聯苯醚 / Heptabromodiphenyl ether	mg/kg	by GC/ MG.	5	n. d.	-
八溴聯苯醚 / Octabromodiphenyl ether	mg/kg		5	n. d.	_
九溴聯苯醚 / Nonabromodiphenyl ether	mg/kg		5	n. d.	_
十溴聯苯醚 / Decabromodiphenyl ether	mg/kg		5	n. d.	_
鄰苯二甲酸丁苯甲酯 / BBP (Butyl Benzy phthalate) (CAS No.: 85-68-7)	/l mg/kg	参考IEC 62321-8/CD (2013),以氣相層析儀/質譜儀檢測. / With reference to IEC 62321-8/CD (2013). Analysis was performed by GC/MS.	50	n. d.	1000
鄰苯二甲酸二丁酯 / DBP (Dibutyl phthalate) (CAS No.: 84-74-2)	mg/kg		50	n. d.	1000
鄰苯二甲酸二異丁酯 / DIBP (Di-isobuty phthalate) (CAS No.: 84-69-5)	yl mg/kg		50	n. d.	1000
鄰苯二甲酸二 (2-乙基己基)酯 / DEHP (Di- (2-ethylhexyl) phthalate) (CAS No.: 117-81-7)	mg/kg		50	n. d.	1000
鹵素 / Halogen					
鹵素 (氟) / Halogen-Fluorine (F) (CAS No.: 14762-94-8)	mg/kg	参考BS EN 14582 (2007),以離子層析 儀分析. / With reference to BS EN 14582 (2007). Analysis was performed by IC.	50	n. d.	-
鹵素 (氣) / Halogen-Chlorine (C1) (CAS No.: 22537-15-1)			50	n. d.	-
鹵素(溴)/ Halogen-Bromine (Br) (CAS No.: 10097-32-2)	mg/kg		50	n. d.	-
鹵素(碘)/ Halogen-Iodine(I)(CAS No.: 14362-44-8)	S mg/kg		50	n. d.	-

日期(Date): 2017/02/15



Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

號碼(No.): CE/2017/21498



頁數(Page): 4 of 15

測試項目 (Test Items)	單位 (Unit)	測試方法 (Method)	方法偵測 極限值 (MDL)	結果 (Result) No.1	限值 (Limit)
全氟辛烷磺酸 / Perfluorooctane sulfonates (PFOS-Acid, Metal Salt, Amide)	mg/kg	參考US EPA 3550C (2007),以液相層析/質譜儀檢測. / With reference to US EPA 3550C (2007). Analysis was	10	n. d.	1
全氟辛酸 / PFOA (CAS No.: 335-67-1)	mg/kg	performed by LC/MS.	10	n. d.	-
聚氯乙烯 / PVC	**	以紅外光譜分析及焰色法檢測. / Analysis was performed by FTIR and FLAME Test.	-	Negative	-
多氣聯苯 / Polychlorinated Biphenyls (PCBs) (CAS No.: 1336-36-3)	mg/kg		0.5	n. d.	-
多氣奈 / Polychlorinated Naphthalene (PCNs)	mg/kg	參考US EPA 3550C (2007),以氣相層	5	n. d.	-
多氯三聯苯 / Polychlorinated Terphenyls (PCTs)	mg/kg	析/質譜儀檢測. / With reference to US EPA 3550C (2007). Analysis was performed by GC/MS.	0.5	n. d.	-
短鏈氯化石蠟 / Alkanes, C10-13, chloro (Short Chain Chlorinated Paraffins) (CAS No.: 85535-84-8)	mg/kg	performed by 66/ mo.	100	n. d.	-

日期(Date): 2017/02/15

備註(Note):

- 1. mg/kg = ppm; 0. 1wt% = 1000ppm
- 2. n.d. = Not Detected (未檢出)
- 3. MDL = Method Detection Limit (方法偵測極限值)
- 4. "-" = Not Regulated (無規格值)
- 5. **= Qualitative analysis (No Unit) 定性分析(無單位)
- 6. Negative = Undetectable 陰性(未偵測到); Positive = Detectable 陽性(已偵測到)

PFOS参考資訊(Reference Information): 持久性有機污染物 POPs - (EU) 757/2010

PFOS濃度在物質或製備中不得超過0.001%(10ppm),在半成品、成品或零部件中不得超過0.1%(1000ppm),在紡織品或塗層 材料中不得超過lug/m2。

(Outlawing PFOS as substances or preparations in concentrations above 0.001% (10ppm), in semi-finished products or articles or parts at a level above 0.1%(1000ppm), in textiles or other coated materials above $1\mu g/m^2$.)



Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN



頁數(Page): 5 of 15

<u>重金屬流程圖 / Analytical flow chart of Heavy</u> Metal


日期(Date): 2017/02/15

根據以下的流程圖之條件,樣品已完全溶解。(六價鉻測試方法除外)

號碼(No.): CE/2017/21498

These samples were dissolved totally by pre-conditioning method according to below flow chart. (Cr^{6^+} test method excluded)

- 測試人員:王志瑋 / Technician : JR Wang
- 測試負責人:張啟興 / Supervisor: Troy Chang



Note** (For IEC 62321)

- (1) 針對非金屬材料加入鹼性消化液,加熱至 90~95℃ 萃取. / For non-metallic material, add alkaline digestion reagent and heat to 90~95℃
- (2) 針對金屬材料加入純水,加熱至沸騰萃取. / For metallic material, add pure water and heat to boiling.



Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

頁數(Page): 6 of 15

多溴聯苯/多溴聯苯醚分析流程圖 / Analytical flow chart - PBB/PBDE


日期(Date): 2017/02/15

測試人員: 涂雅苓 / Technician: Yaling Tu

測試負責人:張啟興 / Supervisor: Troy Chang

號碼(No.): CE/2017/21498

初次測試程序 / First testing process _ 確認程序 / Confirmation process - - - →





Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

頁數(Page): 7 of 15

可塑劑分析流程圖 / Analytical flow chart - Phthalate


日期(Date): 2017/02/15

測試人員:徐毓明 / Technician: Andy Shu

號碼(No.): CE/2017/21498

測試負責人:張啟興 / Supervisor: Troy Chang

【測試方法/Test method: IEC 62321-8】





Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

號碼(No.): CE/2017/21498


頁數(Page): 8 of 15

鹵素分析流程圖 / Analytical flow chart - Halogen

日期(Date): 2017/02/15

測試人員: 陳恩臻 / Technician: Rita Chen

測試負責人:張啟興 / Supervisor: Troy Chang





Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

頁數(Page): 9 of 15

全氟辛酸/全氟辛烷磺酸分析流程圖 / Analytical flow chart - PFOA/PFOS

日期(Date): 2017/02/15

測試人員:涂雅苓 / Technician: Yaling Tu

號碼(No.): CE/2017/21498

測試負責人:張啟興 / Supervisor: Troy Chang

樣品前處理 / Sample pretreatment 超音波萃取法萃取 / Sample extraction by Ultrasonic extraction (參考方法 Reference method: US EPA 3550C) 萃取液稀釋/濃縮 / Concentrate/Dilute Extracted solution

> 以液相層析質譜儀分析萃取液 / Analysis was performed by LC/MS

> > 數據 / Data





Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

號碼(No.): CE/2017/21498


頁數(Page): 10 of 15

聚氯乙烯物質判定分析流程圖 / Analysis flow chart - PVC

日期(Date): 2017/02/15

測試人員:涂雅苓 / Technician: Yaling Tu

測試負責人:張啟興 / Supervisor: Troy Chang





Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN


號碼(No.): CE/2017/21498

頁數(Page): 11 of 15

多氯聯苯分析流程圖 / Analytical flow chart - PCBs

日期(Date): 2017/02/15

- 測試人員:涂雅苓 / Technician: Yaling Tu
- 測試負責人:張啟興 / Supervisor: Troy Chang







Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

號碼(No.): CE/2017/21498

頁數(Page): 12 of 15

<u>多氯奈分析流程圖 / Analytical flow chart - PCNs</u>

日期(Date): 2017/02/15

- 測試人員:涂雅苓 / Technician: Yaling Tu
- 測試負責人:張啟興 / Supervisor: Troy Chang

樣品前處理 / Sample pretreatment 樣品萃取 Sample extraction / 超音波萃取法 Ultrasonic method 萃取液濃縮/稀釋 / Concentrate/Dilute Extracted solution 萃取液過濾 / Filter 以氣相層析/質譜儀分析 / Analysis was performed by GC/MS 數據 / Data





Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

號碼(No.): CE/2017/21498

頁數(Page): 13 of 15 日期(Date): 2017/02/15

多氯三聯苯分析流程圖 / Analytical flow chart - PCTs

測試人員:曾勃鈞 / Technician: Barry Tseng

測試負責人:張啟興 / Supervisor: Troy Chang

樣品前處理 / Sample pretreatment 樣品萃取 Sample extraction / 超音波萃取法 Ultrasonic method 萃取液濃縮/稀釋 / Concentrate/Dilute Extracted solution 萃取液過濾 / Filter

> 以氣相層析/質譜儀分析 / Analysis was performed by GC/MS

> > 數據 / Data





Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號

NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

號碼(No.): CE/2017/21498




頁數(Page): 14 of 15

氯化石蠟分析流程圖 / Analytical flow chart - Chlorinated Paraffins

日期(Date): 2017/02/15

■ 測試人員:涂雅苓 / Technician: Yaling Tu

測試負責人:張啟興 / Supervisor: Troy Chang







Test Report

南亞塑膠工業股份有限公司 NAN YA PLASTICS CORPORATION 新北市泰山區南林路102號 NO. 102, NANLIN RD., TAISHAN DIST., NEW TAIPEI CITY, TAIWAN

號碼(No.): CE/2017/21498




頁數(Page): 15 of 15

* 照片中如有箭頭標示,則表示為實際檢測之樣品/部位. * (The tested sample / part is marked by an arrow if it's shown on the photo.)

日期(Date): 2017/02/15

CE/2017/21498



** 報告結尾 (End of Report) **

